

SURFACE VEHICLE RECOMMENDED PRACTICE

Submitted for recognition as an American National Standard

SAE J444

REV.
MAY93

Issued 1946-01
Revised 1993-05-03

Superseding J444 AUG84

(R) CAST SHOT AND GRIT SIZE SPECIFICATIONS FOR PEENING AND CLEANING

AN AMERICAN NATIONAL STANDARD

- 1. Scope**—This SAE Recommended Practice pertains to blast cleaning and shot peening and provides for standard cast shot and grit size numbers. For shot, this number corresponds with the opening of the nominal test sieve, in ten thousandths of inches¹, preceded by an S. For grit, this number corresponds with the sieve designation of the nominal test sieve with the prefix G added. These sieves are in accordance with ASTM E 11.

The accompanying shot and grit classifications and size designations were formulated by representatives of shot and grit suppliers, equipment manufacturers, and automotive users.

2. References

- 2.1 Applicable Document**—The following publication forms a part of this specification to the extent specified herein.

- 2.1.1 ASTM PUBLICATION**—Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM E 11—Standard Specifications for Wire Cloth Sieves for Testing Purposes

- 2.2 Related Publications**—The following publications are provided for information purposes only and are not a required part of this document. The latest issue of SAE publications shall apply.

- 2.2.1 SAE PUBLICATIONS**—Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

SAE J445—Metallic Shot and Grit Mechanical Testing—For Information on Shot Durability Determination

SAE J827—Cast Steel Shot—For Information on Composition and Shapes

SAE J1993—Cast Steel Grit—For Information on Composition and Shapes

SAE J2175—Low Carbon Steel Shot—For Information on Composition and Shapes

3. Testing Procedure—Sieve Analysis

3.1 Equipment

**CONTROLLED
DOCUMENT**

¹ Example: S-550 indicates a cast steel shot identified by a nominal sieve opening of 0.0555 in.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

3.1.1 A rotating and tapping type of testing machine shall be used.

3.1.1.1 The shaking speed shall be 275 to 295 rpm.

3.1.1.2 The taps per minute shall be 145 to 160 when tapping machines are used.

3.2 Sieves

3.2.1 The testing sieves shall be in accordance with ASTM E 11. They shall be of the 203 mm (8 in) diameter series, of either 25 mm (1 in) or 51 mm (2 in) height.

3.3 Procedure

3.3.1 A 100 g sample of the shot or grit shall be obtained from a representative quantity.

3.3.2 The sample shall be placed on the top sieve of a stack of three or four sieves, depending on media and size (Figures 1 and 2). Nest the selected sieves and fit a pan to the bottom sieve.

3.3.3 The sample shall be run in the testing machine for 5 min \pm 5 s for sizes using sieve designation 35 or coarser and 10 min \pm 5 s for sizes using sieve designation finer than 35.

3.3.4 The stack of sieves shall be removed from the testing machine and the percentage of total weight shall be recorded for the media remaining on each sieve.

3.4 Any alternate method agreed upon by the supplier and the user which gives equivalent results will be acceptable.

4. Notes

4.1 **Marginal Indicia**—The (R) is for the convenience of the user in locating areas where technical revisions have been made to the previous issue of the report. If the symbol is next to the report title, it indicates a complete revision of the report.

PREPARED BY THE SAE FATIGUE, DESIGN, AND EVALUATION COMMITTEE

FIGURE 1—CAST SHOT SPECIFICATIONS FOR SHOT PEENING OR BLAST CLEANING

Sieve Opening Standard	Sieve Designation	Nominal Sieve Opening (in)	Test Sieve Opening Size and Designation With Maximum and Minimum Cumulative Percentages Allowed on Corresponding Test Sieves SAE Shot Number																				
			S1320	S1110	S930	S780	S660	S550	S460	S390	S330	S280	S230	S170	S110	S70							
4.75	4	(0.187)	All Pass	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-				
4.00	5	(0.157)	-	All Pass	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-				
3.35	6	(0.132)	90% min	-	All Pass	-	-	-	-	-	-	-	-	-	-	-	-	-	-				
2.80	7	(0.111)	97% min	90% min	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-				
2.36	8	(0.0937)	-	97% min	90% min	-	-	-	-	-	-	-	-	-	-	-	-	-	-				
2.00	10	(0.0787)	-	-	97% min	85% min	-	All Pass	-	-	-	-	-	-	-	-	-	-	-				
1.70	12	(0.0661)	-	-	97% min	97% min	85% min	85% min	-	-	-	-	-	-	-	-	-	-	-				
1.40	14	(0.0555)	-	-	-	97% min	97% min	97% min	85% min	5% max	-	-	-	-	-	-	-	-	-				
1.18	16	(0.0469)	-	-	-	-	-	-	85% min	85% min	5% max	-	-	-	-	-	-	-	-				
1.00	18	(0.0394)	-	-	-	-	-	-	-	85% min	85% min	5% max	-	-	-	-	-	-	-				
0.850	20	(0.0331)	-	-	-	-	-	-	-	96% min	96% min	85% min	5% max	-	-	-	-	-	-				
0.710	25	(0.0278)	-	-	-	-	-	-	-	-	96% min	96% min	85% min	85% min	10% max	-	-	-	-				
0.600	30	(0.0234)	-	-	-	-	-	-	-	-	-	96% min	96% min	85% min	85% min	10% max	-	-	-				
0.500	35	(0.0197)	-	-	-	-	-	-	-	-	-	-	96% min	96% min	85% min	85% min	10% max	-	-				
0.425	40	(0.0165)	-	-	-	-	-	-	-	-	-	-	-	96% min	96% min	85% min	85% min	10% max	-				
0.355	45	(0.0139)	-	-	-	-	-	-	-	-	-	-	-	-	96% min	96% min	85% min	85% min	10% max	-			
0.300	50	(0.0117)	-	-	-	-	-	-	-	-	-	-	-	-	-	96% min	96% min	85% min	85% min	10% max			
0.180	80	(0.0070)	-	-	-	-	-	-	-	-	-	-	-	-	-	-	96% min	96% min	85% min	85% min	10% max		
0.125	120	(0.0049)	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	96% min	96% min	85% min	85% min	10% max	
0.075	200	(0.0029)	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	96% min	96% min	85% min	85% min	10% max

¹ Corresponds to ISO Recommendations

Rationale—Not applicable.

Relationship of SAE Standard to ISO Standard—Not applicable.

Application—This SAE Recommended Practice pertains to blast cleaning and shot peening and provides for standard cast shot and grit size numbers. For shot, this number corresponds with the opening of the nominal test sieve, in ten thousandths of inches¹, preceded by an S. For grit, this number corresponds with the sieve designation of the nominal test sieve with the prefix G added. These sieves are in accordance with ASTM E 11.

The accompanying shot and grit classifications and size designations were formulated by representatives of shot and grit suppliers, equipment manufacturers, and automotive users.

Reference Section

SAE J445—Metallic Shot and Grit Mechanical Testing—For Information on Shot Durability Determination

SAE J827—Cast Steel Shot—For Information on Composition and Shapes

SAE J1993—Cast Steel Grit—For Information on Composition and Shapes

SAE J2175—Low Carbon Steel Shot—For Information on Composition and Shapes

ASTM E 11—Standard Specifications for Wire Cloth Sieves for Testing Purposes

Developed by the SAE Fatigue, Design, and Evaluation Committee